






PRIMUS, naturally oiled



Tests	DIN / EN standard	HAIN Parquet flooring PRIMUS, naturally oiled
General data on product composition		
Type of covering:		Flooring panel with top layer made from fine wood
Total thickness:		approx. 12 mm
Effective measurement: (length × width)		2 200 × 160 mm (each parquet plank can be included in the package as two half-planks)
Product structure:		a. Naturally oiled surface b. Approx. 4 mm fine wood wear layer c. Spruce middle layer d. Backing (Nordic spruce veneer)
Technical data		
 Fire behaviour:	EN 13501	D _{fl} -s1 (hardly flammable) with full-surface bonding using the glue HAIN Elastic shear-resistant
 Formaldehyde emissions (E1 = 0.1 ppm):	EN 717-1	E1
 Content of pentachlorophenol:	CEN/TR 14823	≤ 5 × 10 ⁻⁶ m
 Underfloor heating:		Please follow the separate briefing sheets for installation on hot-water underfloor heating and over electrical underfloor heating systems
Underfloor cooling:		A separate leaflet is available for laying on cooled floor constructions
Heat transfer resistance:	EN 12664	0.11 m ² K/W
Thermal conductivity:	EN 12664	0.112 W/mK
Antislip inclined plane:	DIN 51130 BGR 181	R10 (oak with brushed surface)
General data on environment, installation and care		
Blue Angel:	RAL-UZ 176	awared (except for smoked surfaces)
Disposal:		Residual pieces can be disposed of in household refuse (e.g. thermal treatment). Dispose large quantities according to municipal provisions (e.g. recycling centres). An energetic utilisation in authorised plants is recommended.
Cleaning and care:		Cleaning after construction work / maintenance cleaning: HAIN Special soap Basic cleaning: HAIN Basic cleaner Care: HAIN Care balm



HAIN Naturböden GmbH & Co. KG reserves the right to make alterations to material and structures when this serves to improve the quality.